

SIGMADUR™ 550 H

(SIGMADUR™ 568)

DESCRIPTION

Two-component, high solids, high-build aliphatic acrylic polyurethane finish

PRINCIPAL CHARACTERISTICS

- Excellent resistance to atmospheric exposure conditions
- Good color and gloss retention
- Cures at temperatures down to -5°C (23°F)
- Resistant to splash of mineral and vegetable oils, paraffins, aliphatic petroleum products and mild chemicals
- Can be recoated even after long atmospheric exposure
- Good application properties by airless, brush and roller
- High film build-up to 150 µm (6.0 mils) for one coat
- Can be applied direct to metal
- Drying and curing times can be reduced significantly using PPG 866M ACCELERATOR

COLOR AND GLOSS LEVEL

- Standard and custom colors
- Gloss

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.5 kg/l (12.5 lb/US gal)
Volume solids	70 ± 2%
VOC (Supplied)	Directive 1999/13/EC, SED: max. 220.0 g/kg max. 330.0 g/l (approx. 2.8 lb/US gal) UK PG 6/23(92) Appendix 3: max. 259.0 g/l (approx. 2.2 lb/US gal)
Recommended dry film thickness	50 - 150 µm (2.0 - 6.0 mils) depending on system
Theoretical spreading rate	14.0 m ² /l for 50 µm (561 ft ² /US gal for 2.0 mils) 9.3 m ² /l for 75 µm (374 ft ² /US gal for 3.0 mils)
Overcoating Interval	Minimum: 8 hours Maximum: Unlimited
Shelf life	Base: at least 36 months when stored cool and dry Hardener: at least 24 months when stored cool and dry

Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time



SIGMADUR™ 550 H

(SIGMADUR™ 568)

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions

- Steel; blast cleaned to ISO-Sa2½, blasting profile 40 – 70 µm (1.6 – 1.8 mils), or powertool cleaned to ISO-St3
 - Compatible previous coat must be dry and free from any contamination
-

Substrate temperature and application conditions

- Substrate temperature during application and curing should be at least 3°C (5°F) above dew point
 - Substrate temperature during application and curing down to -5°C (23°F) is acceptable; provided the substrate is free from ice and dry
 - Relative humidity during application and curing should not exceed 85%
 - Premature exposure to early condensation and rain may cause color and gloss change
-

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 87:13

- Do not thin more than is required by appropriate application property
 - Adding too much thinner results in reduced sag resistance
 - Thinner should be added after mixing the components
-

Induction time

None

Air spray

Recommended thinner

THINNER 21-06

Volume of thinner

10 - 15%, depending on required thickness and application conditions

Nozzle orifice

1.0 - 1.5 mm (approx. 0.040 - 0.060 in)

Nozzle pressure

0.3 - 0.4 MPa (approx. 3 - 4 bar; 44 - 58 p.s.i.)

SIGMADUR™ 550 H

(SIGMADUR™ 568)

Airless spray

Recommended thinner

THINNER 21-06

Volume of thinner

0 - 10%, depending on required thickness and application conditions

Nozzle orifice

Approx. 0.43 – 0.48 mm (0.017 – 0.019 in)

Nozzle pressure

20.0 MPa (approx. 200 bar; 2901 p.s.i.)

Brush/roller

Recommended thinner

THINNER 21-06

Volume of thinner

0 – 5%

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
50 µm (2.0 mils)	14.0 m ² /l (561 ft ² /US gal)
75 µm (3.0 mils)	9.3 m ² /l (374 ft ² /US gal)
100 µm (4.0 mils)	7.0 m ² /l (281 ft ² /US gal)
150 µm (6.0 mils)	4.7 m ² /l (187 ft ² /US gal)

Overcoating interval for DFT up to 150 µm (6.0 mils)							
Overcoating with...	Interval	-5°C (23°F)	0°C (32°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself	Minimum	36 hours	24 hours	16 hours	8 hours	4 hours	3 hours
	Maximum	Unlimited	Unlimited	Unlimited	Unlimited	Unlimited	Unlimited

SIGMADUR™ 550 H

(SIGMADUR™ 568)

Overcoating interval with PPG 866M ACCELERATOR for DFT up to 150 µm (6.0 mils)

Overcoating with...	Interval	-5°C (23°F)	0°C (32°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself	Minimum	28 hours	20 hours	12 hours	6 hours	3 hours	1.5 hours
	Maximum	Unlimited	Unlimited	Unlimited	Unlimited	Unlimited	Unlimited

Note: Surface should be dry and free from any contamination

Curing time for DFT up to 150 µm (6.0 mils)

Substrate temperature	Dry to touch	Dry to handle	Full cure
-5°C (23°F)	24 hours	40 hours	22 days
0°C (32°F)	15 hours	30 hours	18 days
10°C (50°F)	5 hours	20 hours	10 days
20°C (68°F)	3 hours	12 hours	7 days
30°C (86°F)	2 hours	6 hours	4 days
40°C (104°F)	1 hour	3 hours	3 days

Curing time with PPG 866M ACCELERATOR for DFT up to 150 µm (6.0 mils)

Substrate temperature	Dry to touch	Dry to handle	Full cure
-5°C (23°F)	21 hours	32 hours	18 days
0°C (32°F)	12 hours	24 hours	15 days
10°C (50°F)	4 hours	15 hours	8 days
20°C (68°F)	2 hours	8 hours	6 days
30°C (86°F)	1.5 hours	4 hours	3 days
40°C (104°F)	1 hour	2 hours	48 hours

Notes:

- Adequate ventilation must be maintained during application and curing (please refer to INFORMATION SHEETS 1433 and 1434)
- Premature exposure to early condensation and rain may cause color and gloss change

Pot life (at application viscosity)

Mixed product temperature	Pot life
10°C (50°F)	4 hours
20°C (68°F)	2.5 hours
30°C (86°F)	1.5 hours
40°C (104°F)	1 hour

Note: Mixing this product with PPG 866M ACCELERATOR will not affect the pot life



SIGMADUR™ 550 H

(SIGMADUR™ 568)

SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes
- Contains a toxic polyisocyanate curing agent
- Avoid at all times inhalation of aerosol spray mist

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431
• SAFE WORKING IN CONFINED SPACES	INFORMATION SHEET	1433
• DIRECTIVES FOR VENTILATION PRACTICE	INFORMATION SHEET	1434

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG Logo, Bringing innovation to the surface., and all other trademarks herein are property of the PPG group of companies.



**PPG Protective &
Marine Coatings**

Bringing innovation to the surface.™