

# SIGMAGLIDE® 890

## DESCRIPTION

Two-component, silicone-based finish for fouling release system

## PRINCIPAL CHARACTERISTICS

- Non-toxic, fouling release coating for ships, installations and seawater intakes under all fouling conditions
- For use at new-building or maintenance

## COLOR AND GLOSS LEVEL

- Redbrown (other colors available on request)
- Gloss

## BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.1 kg/l (9.2 lb/US gal)
Volume solids	77 ± 2%
VOC (Supplied)	Directive 1999/13/EC, SED: max. 196.0 g/kg max. 215.0 g/l (approx. 1.8 lb/US gal)
Recommended dry film thickness	150 µm (6.0 mils)
Theoretical spreading rate	5.1 m <sup>2</sup> /l for 150 µm (206 ft <sup>2</sup> /US gal for 6.0 mils)
Dry to touch	1 hour
Overcoating Interval	Minimum: 2 hours
Refloating time	Minimum: 8 hours
Shelf life	Base: at least 36 months when stored cool and dry Hardener: at least 36 months when stored cool and dry

Note: See ADDITIONAL DATA – Overcoating intervals

## RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

### Substrate conditions

- For new-buildings or spot/full blast, SIGMAGLIDE 890 should only be applied over SIGMAGLIDE 790
- As a refresh coat, SIGMAGLIDE 890 can be applied over itself in line with PPG Protective & Marine Coatings SIGMAGLIDE General Working Procedure
- Previous coat must be dry and free from any contamination

# SIGMAGLIDE® 890

## **Substrate temperature and application conditions**

- Substrate temperature during application and curing should be above 5°C (41°F)
  - Substrate temperature during application and curing should be at least 3°C (5°F) above dew point
  - Relative humidity during application and curing should be between 40% and 85%
- 

## **SYSTEM SPECIFICATION**

- SIGMAGLIDE FOULING RELEASE COATING SYSTEM – SYSTEM SHEET 3127
  - In order to achieve optimal performance from the SIGMAGLIDE system, the individual SIGMAGLIDE products must be applied in strict accordance with the minimum specified dry film thickness and also with the PPG Protective & Marine Coatings SIGMAGLIDE General Working Procedure. Please consult PPG Protective & Marine Coatings for details of the application procedure which has been prepared to the best of our knowledge and in accordance with worldwide application best practices in order to ensure optimal workmanship and application results.
- 

## **INSTRUCTIONS FOR USE**

### **Mixing ratio by volume: base to hardener 80:20 (4:1)**

- Open drum just before use
  - Stir base well before use for 5 minutes
  - Add hardener to the base and stir well again for at least 5 minutes
  - No thinner should be added
  - All equipment must be thoroughly cleaned prior to use and before re-use with other materials, to prevent contamination
  - Overspray on paint, which will not be recoated with the SIGMAGLIDE 890, should be avoided as much as possible
- 

### **Induction time**

None

---

### **Pot life**

4 hours at 20°C (68°F)

Note: See ADDITIONAL DATA – Pot life

---

# SIGMAGLIDE® 890

## Airless spray

### Recommended thinner

No thinner should be added

### Nozzle angle

35° – 60°, depending on nozzle orifice

### Nozzle orifice

Approx. 0.43 – 0.53 mm (0.017 – 0.021 in)

### Nozzle pressure

15.0 - 20.0 MPa (approx. 150 - 200 bar; 2176 - 2901 p.s.i.)

## Brush/roller

- For small areas only (touch up and repair)

## Cleaning solvent

THINNER 90-83 or 50/50 mixture of THINNER 21-06 and THINNER 50-02

Note: please note that used cleaning solvent must not be allowed to contaminate other paints

## ADDITIONAL DATA

Overcoating interval for DFT up to 150 µm (6.0 mils)					
Overcoating with...	Interval	10°C (50°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself	Minimum	3 hours	2 hours	1 hour	1 hour
	Maximum	8 hours	8 hours	8 hours	8 hours

### Notes:

- Surface should be dry and free from any contamination
- Relative humidity should be above 40%

Pot life (at application viscosity)	
Mixed product temperature	Pot life
10°C (50°F)	6 hours
20°C (68°F)	4 hours
30°C (86°F)	2 hours

# SIGMAGLIDE® 890

## SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

## WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

## REFERENCES

• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431
• PPG PROTECTIVE & MARINE COATINGS' GENERAL WORKING PROCEDURES FOR APPLICATION OF SIGMAGLIDE®		

## WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

## LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at [www.ppgpmc.com](http://www.ppgpmc.com). The English text of this sheet shall prevail over any translation thereof.

The PPG Logo, Bringing innovation to the surface., and all other trademarks herein are property of the PPG group of companies.